

UP sticker adhesion and perspiration resistance tests

【Test method】

(Step1)

Criss cross cut was made in the UP sticker on the acetate temple with a box cutter as shown in the picture.

(Step2)

A taping test was performed on the cross-cut area after a 24-hour sweat test.

Note: We performed the test using the Leaf vein pattern and Alphabet logo because the UP sticker with detailed patterns or logos is often used.



【Test result】

Leaf vein pattern



Alphabet logo



There was no surface peeling of either UP sticker.

